

ERLING TechnoFloor® HardTop Extra

Non-metallic, Dry shake Monolithic Concrete Floor Hardener.

Description:

TechnoFloor® Hardtop Extra is a pre-blended, ready to use and dry shake formulation for hardening freshly placed horizontal concrete slabs and toppings. TechnoFloor® Hardtop Extra contains specially selected aggregates with excellent abrasion and wear resistance along with cementitious binders, plasticizers and admixtures to provide a tough & durable floor.

TechnoFloor® Hardtop Extra produces a hard, dense, wear resistant surface which resists corrosion and absorption of grease, oils, alkalis and most chemicals.

Application Includes:

TechnoFloor® Hardtop Extra used for providing a high wear resistant and antiskid surface to newly laid concrete surface by the dry shake method. It finds its best use in indoor and outdoor applications wherever heavy-duty floor finish is required such as-

- Industrial warehouses & factories
- Garages
- Ramps and loading bays & car parks.
- Power stations
- Aircraft hangers

Features:

- Premixed, ready to use offering factory controlled quality assurance
- Ease of application
- Non-dusting surface
- Non-oxidizing
- Slip-resistant finish can be obtained
- For internal and external use
- Provides a monolithic hardening surface within the concrete matrix
- Provides a hard, abrasion resistant, wear resistant surface
- Provides high impact resistance

Shelf Life

TechnoFloor® Hardtop Extra has a shelf life of 12 months when stored in cool and dry conditions. Extreme temperature, excessive humidity and over exposure to UV will result in the reduction of shelf life.

Packaging

 $\ensuremath{\mathsf{TechnoFloor}}\xspace{1.5mu}{\mathbb{R}}$ Hardtop Extra is supplied in 30 kg bags.

Instructions for Use

Use a placable and finishable non-bleeding concrete mix of required strength design, with a minimum slump of 75 mm and not more than 3% entrained air. The surface is then floated with a wooden or aluminum float. After casting, any bleeding water from the concrete should be removed.

Sprinkle TechnoFloor $\$ Hardtop Extra along edges of bags (approx. 100 mm strips) where expansion and contraction joints will be located first. Float into surface using a wooden float.

As soon as the concrete is firm enough to support the weight of the workman, apply the first shake of TechnoFloor(R) Hardtop Extra.

Use up to 2/3 of the total shake mix in the first application. Treat areas adjacent to walls and columns first. Spread the material evenly by sprinkling at right angles in two passes close to the floor level. Allow applied material to absorb moisture from the concrete surface. Uniform darker color will be apparent.

Using a wooden float, float TechnoFloor® Hardtop Extra into the concrete ensuring material becomes an integral part of the surface. Follow second floating immediately after first floating. Employ the balance of the material, follow promptly with second floating using wood or aluminum float or power float in case of large areas. A third power floating may follow for added compaction, if required.

Note: If coarse non-slip finish is required, do not proceed with further floating or trowelling operations after second floating but allow the surface to cure.

Curing

Curing should be carried out immediately after the final trowelling operation has been completed. It can be done by either covering with wet Hessian cloth and Polythene sheets or by the application of TechnoFinish® Conkure 101/102 curing compound. Immediately after removing Polythene sheet sweep the floor to remove any dust or loose particles.

Typical Properties at 25°C:

Appearance / Colors	Cement Gray Powder (other colours available on request)
Chemic Base	Natural mineral aggregates graded and mixed with cement, admixtures and pigments.
Hardness (Aggregate)	7-8 (Mohs scale of hardness)
Curing	Required
Application rate(kg/m2)	Light traffic 3kg/m2 Medium traffic 5kg/m2 Heavy traffic 7kg/m2
Abrasion Resistance	1.70 mm thickness loss (average) (According to IS 1237- 1980)
Bulk Density	1.5 ± 0.1 kg/l at 27°C
Compressive Strength	At7 days >40 N/mm² (ASTM C579) At28 days >50 N/mm²(ASTM C579)
Flexural Strength	At7 days >7 N/mm ² (ASTM C580) At28 days >11 N/mm(ASTM C580)
All values are subject to 5-10 % tolerance	

Recommendations

Ensure that enough labor, machinery and material is available to complete treating the whole area before concrete dries

Do not use TechnoFloor® Hardtop Extra areas exposed to acids.

In case of coloured floor, test a small area of floor to ensure the color integrity

Fire

TechnoFloor® Hardtop Extra is non-flammable.

Storage

Store in dry conditions between 5° C and 30°C, away from sources of heat and naked flames, in the original, unopened packs. If stored at high temperatures the shelf life will be reduced.

Cleaning

Tools and equipment should be cleaned with water after use. Spillages should be absorbed with sand or sawdust and disposed of in accordance with local regulations. Hardened materials should be removed mechanically.

Product only for professional use.

Health and Safety instructions

TechnoFloor® Hardtop Extra contains Portland cement and are therefore alkaline when in contact with water. Prolonged contact with the skin should be avoided. During application, wear appropriate protective clothing, goggles, gloves and respiratory equipment. Any eye contamination should be washed immediately with plenty of clean water and medical advice sought.

Additional Information: Techno Builders Solutions[®] By Sterling Technotrade India Pvt.Ltd -The Specialist Construction Chemicals Company[®] range of associated products includes high performance concrete Admixtures, Adhesives, Protective Coatings, Concrete Repairs, Industrial Flooring, Grouts & Anchors, Joint Sealants, Surface Treatments, curing compounds, repair mortars, release agents, Grinding Aids & Waterproofing.

*Separate datasheet are available on these products.

Caution

Timing of the broadcast is very important in the application of TechnoFloor® Hardtop Extra. Care should be taken that adequate labor, material and machinery is available to complete the whole area while the moisture is still available for the material to fully react and form the required finish. Conversely, full benefit will not be achieved if the material is applied too early when bleed water is still present. Never apply additional water to aid finishing as this could prove detrimental to the whole system and also result in a patchy surface while using colored TechnoFloor® Hardtop Extra.

Precautions & Limitations

Not for use where operating and service conditions dictate the use of a metallicaggregate surface hardener for greater abrasion and impact resistance. Not for use in areas exposed to acids and their salts or to materials known to rapidly attack or deteriorate Portland cement concrete.

DISCLAIMER: The product information & application details given by the company & its agents has been provided in good faith & meant to serve only as a general guideline during usage. Users are advised to carry out tests & take trials to ensure on the suitability of products meeting their requirement prior to full scale usage of our products. Since the correct identification of the problems, quality of other materials used and the on-site workmanship are factors beyond our control, there are no expressed or implied guarantee / warranty as to the results obtained. The company does not assume any liability or consequential damage for unsatisfactory results, arising from the use of our products.

EDITION: 02/2018/001

IDENTIFICATION NO: PD-183

Please note that this datasheet supersedes all previous versions.

STERLING TECHNOTRADE INDIA PRIVATE LIMITED The Specialist Construction Chemical Company[®]

Head Office: 109-111-112, 1st Floor, Vijaya Building, No. 17, Barakhamba Road, Connaught Place, New Delhi- 110001
Manufacturing Unit: Plot No-J-3, UPSIDC Site C, Surajpur Industrial Area, Greater Noida, Uttar Pradesh 201306
WEB: sterlingtechnotrade.com | EMAIL: support@sterlingtechnotrade.com | TEL: 01145084212